

Dimensiones y peso línea tubería de acero al carbón e inox.,
con y sin costura, uso ordinario, según fórmula específico 7850 kg/m³
y tablas ASME B36. 19M y API 5L



Diámetro Nominal in	Diámetro Exterior Outside Diameter		Espesor de pared Wall thickness		Cédula Schedule/ Designation	Weight	Peso
	in	mm	in	mm		lb/ft	Kg/m
1/8	0.045	10.3	0.068	1.73	40 40S STD	0.24	0.36
			0.095	2.41	80 80S XS	0.31	0.47
1/4	0.540	13.7	0.088	2.24	40 40S STD	0.43	0.63
			0.119	3.02	80 80S XS	0.54	0.80
3/8	0.675	17.1	0.091	2.31	40 40S STD	0.57	0.85
			0.126	3.20	80 80S XS	0.74	1.10
1/2	0.840	21.3	0.109	2.77	40 40S STD	0.85	1.27
			0.147	3.73	80 80S XS	1.09	1.62
			0.188	4.76	160	1.31	1.95
3/4	1.050	26.7	0.113	2.87	40 40S STD	1.13	1.68
			0.154	3.91	80 80S XS	1.48	2.20
			0.219	5.56	160	1.95	2.90
1	1.315	33.4	0.133	3.38	40 40S STD	1.68	2.50
			0.179	4.55	80 80S XS	2.17	3.23
			0.250	6.35	160	2.85	4.24
1 1/4	1.660	42.2	0.140	3.56	40 40S STD	2.27	3.39
			0.191	4.85	80 80S XS	3.00	4.46
			0.250	6.35	160	3.77	5.61
1 1/2	1.900	48.3	0.145	3.68	40 40S STD	2.72	4.05
			0.200	5.08	80 80S XS	3.63	5.41
			0.281	7.14	160	4.86	7.24
2	2.375	60.3	0.154	3.91	40 40S STD	3.66	5.44
			0.218	5.54	80 80S XS	5.03	7.48
			0.344	8.74	160	7.47	11.11
2 1/2	2.875	73.0	0.203	5.16	40 40S STD	5.80	8.63
			0.276	7.01	80 80S XS	7.67	11.41
			0.375	9.53	160	10.02	14.91
3	3.500	88.9	0.216	5.49	40 40S STD	7.58	11.28
			0.300	7.62	80 80S XS	10.26	15.27
			0.438	11.13	160	14.34	21.34
4	3.500	88.9	0.237	6.02	40 40S STD	10.80	16.07
			0.337	8.56	80 80S XS	15.00	22.32
			0.531	13.49	160	22.53	33.53
5	5.563	141.3	0.258	6.55	40 40S STD	14.63	21.77
			0.375	9.53	80 80S XS	20.80	30.95
			0.625	15.88	160	32.99	49.10
6	6.625	168.3	0.280	7.11	40 40S STD	18.99	28.26
			0.432	10.97	80 80S XS	28.60	42.56
			0.719	18.26	160	45.39	67.56
8	8.625	219.1	0.322	8.18	40 40S STD	28.58	42.53
			0.500	12.70	80 80S XS	43.43	64.63
			0.906	23.01	160	74.76	111.26